

Las mejores soluciones para ingeniería, alta calidad y el mejor servicio

PYRAMAT® 25 turf reinforcement mat (TRM) is a three-dimensional, lofty, woven polypropylene geotextile that is available in green which is specially designed for erosion control applications on steep slopes and vegetated waterways. The matrix is composed of polypropylene monofilament yarns featuring X3® technology woven into a uniform configuration of resilient pyramid-like projections. The material exhibits very high interlock and reinforcement capacity with both soil and root systems, demonstrates superior UV resistance, and enhances seedling emergence.

PYRAMAT® 25 conforms to the property values listed below¹ and is manufactured at a Propex facility having achieved ISO 9001:2008 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area ²	ASTM D-6566	7.5 oz/yd ²	254 g/m ²
Thickness ²	ASTM D-6525	0.25 in	6.4 mm
Light Penetration (% Passing) ³	ASTM D-6567	35%	35%
Color	Visual	Green or Tan	
MECHANICAL			
Tensile Strength ²	ASTM D-6818	2000 x 1800 lbs/ft	29.2 x 26.3 kN/m
Elongation ²	ASTM D-6818	20 x 20 %	20 x 20 %
Resiliency ²	ASTM D-6524	70%	70%
Flexibility ⁴	ASTM D-6575	0.195 in-lb	225,000 mg-cm
ENDURANCE			
UV Resistance % Retained at 1,000 hrs ⁴	ASTM D-4355	90%	90%
UV Resistance % Retained at 3,000 hrs ⁴	ASTM D-4355	90%	90%
PERFORMANCE			
Velocity (Vegetated) ^{4, 5}	Large Scale	20 ft/sec	6.1 m/sec
Shear Stress (Vegetated) ^{4, 5}	Large Scale	12 lb/ft ²	575 Pa
Manning's n (Unvegetated) ^{4, 6}	Calculated	0.028	0.028
Seedling Emergence ⁴	ASTM D-7322	255%	255%
ROLL SIZES		8.5 ft x 120 ft 15.0 ft x 120 ft	2.6 m x 36.6 m 4.6 m x 36.6 m

NOTES:
 1. The property values listed above are effective 02/08/2017 and are subject to change without notice.
 2. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.